



## Coppercoat Re-application



If the existing Coppercoat is in good condition (no flaking, blistering, or detachment), it can be recoated by following these steps:

### 1. Surface Preparation

Sand the entire surface using 120-grit sandpaper until the finish turns brown. This means all the green oxidation layer has been removed.

### 2. Cleaning

Thoroughly wash the hull with clean water to remove all dust and contaminants. Allow the surface to dry completely.

### 3. Application

Apply a full new treatment of Coppercoat (4-5 coats) in a single day, following the standard application procedure.

### 4. Supports and Missed Areas

After 3 days of curing, lift the boat and reposition the supports. Sand the previously covered areas, clean, dry, and apply Coppercoat using the same method.

### 5. Final Activation and Launch

After a further 3 days, lightly sand the entire hull to activate the Coppercoat surface. The boat is then ready for relaunch.



## Reaplicación de Coppercoat

Si el Coppercoat existente se encuentra en buen estado (sin descamación, ampollas ni desprendimientos), puede reaplicarse siguiendo estos pasos:

### 1. Preparación de la superficie

Lijar toda la superficie con lija de grano 120 hasta que adquiera un tono marrón. Esto indica que se ha eliminado completamente la capa verde de oxidación.

### 2. Limpieza

Lavar el casco con agua limpia para eliminar polvo y cualquier tipo de contaminación. Dejar secar completamente.

### 3. Aplicación

Aplicar un tratamiento completo nuevo de Coppercoat (4-5 capas) en el mismo día, siguiendo el procedimiento estándar de aplicación.

### 4. Soportes y zonas no cubiertas

Tras 3 días de curado, izar la embarcación y mover los soportes. Lijar las zonas que quedaron cubiertas, limpiar, secar y aplicar Coppercoat siguiendo el mismo método.

### 5. Activación final y botadura

Después de otros 3 días, lijar suavemente todo el casco para activar la superficie del Coppercoat. La embarcación estará entonces lista para su botadura.

**Ambientech**

[coppercoat.es](http://coppercoat.es)

**Deportivo Marina Internacional Fase II s/n - Varadero, 03181 Torrevieja, Alicante**

[info@ambientech.es](mailto:info@ambientech.es)